



100 % gekämmte Extralangstapel-Baumwolle, Compact

SwissCotton Compact - 100 % gekämmte Extralangstapel-Baumwolle - Compact: Garnrichtwerte für Konen

| Garnnummer | | | Zugfestigkeit (5000mm/min.) * | | Dehnung * | Egalität ** | Imperfektionen ** | | | Haarigkeit ** |
|------------|-----|-----|-------------------------------|------|-----------|-------------|-------------------|-----------|--------------|---------------|
| Ne | Nm | CV% | cN/tex | CV% | D% | CV% | Dünn -50% | Dick +50% | Nissen +200% | H |
| 30 | 50 | 1.2 | 26.4 | 7.2 | 6.1 | 10.8 | 0 | 5 | 9 | 4.6 |
| 40 | 68 | 1.2 | 27.3 | 7 | 5.9 | 11.6 | 0 | 8 | 20 | 3.4 |
| 50 | 85 | 1.3 | 26.6 | 7.5 | 5.7 | 12.2 | 0 | 20 | 30 | 2.9 |
| 60 | 100 | 1.3 | 25.8 | 7.9 | 5.3 | 12.7 | 2 | 25 | 40 | 3 |
| 70 | 120 | 1.4 | 25.7 | 9.1 | 5.1 | 13.4 | 8 | 35 | 60 | 2.7 |
| 80 | 135 | 1.5 | 25.1 | 9.7 | 5.1 | 13.8 | 15 | 45 | 75 | 2.5 |
| 100 | 170 | 1.7 | 23.7 | 11.4 | 5 | 15 | 45 | 75 | 110 | 2.4 |
| 118 | 220 | 1.8 | 21 | 14.5 | 4.8 | 16.4 | 150 | 140 | 160 | 2.2 |
| 132 | 224 | 2 | 20.5 | 16.5 | 4.6 | 17.3 | 270 | 200 | 200 | 2.1 |

aktualisiert: 6.2.08

* gemessen mit Uster Tensorapid

** gemessen mit Uster Tester 4

Hermann Bühler AG

Spinnerei

8482 Sennhof (Winterthur)

Schweiz

tel. +41/52/234 04 04

fax +41/52/234 04 94

e-mail: info@buhleryarn.com

internet: www.buhleryarn.com