

SwissCotton Silver - 100 % algodón extra larga con X-Static®: Información del hilo en los conos

XA: 95% algodón extra larga / 5% X-Static

XB: 90% algodón extra larga / 10% X-Static

Titulo del Hilo			Resistencia (5000mm/min.) *		Elongación*	Variación masiva **	Imperfecciones **			Vellosidad **
Ne	Nm	CV%	cN/tex	CV%	D%	CV%	Delgados -50%	Gruesos +50%	Motas +200%	H
16 XA	28	0.8	23.8	5.6	6.4	0.0	0	0	0	6.6
16 XB	28	0.8	23.0	5.8	6.4	0.0	0	0	0	6.4
20 XA	34	0.8	24.4	5.8	6.3	0.0	0	0	0	5.4
20 XB	34	0.8	24.1	6.2	6.4	0.0	0	0	0	5.2
30 XA	50	0.9	23.8	6.4	5.8	0.0	0	0	0	4.7
30 XB	50	0.9	23.8	6.7	5.8	0.0	0	0	0	4.6
40 XA	68	0.9	22.3	7.1	5.5	0.0	0	0	0	4.6
40 XB	68	1.0	22.0	7.2	5.5	0.0	0	0	0	4.2
50 XA	85	1.0	22.2	7.9	5.3	0.0	0	0	0	4.1
60 XA	100	1.0	20.5	8.0	5.2	0.0	0	0	0	4.1
60 XB	100	1.0	19.8	8.2	4.8	0.0	0	0	0	3.9
80 XB	135	1.2	18.0	10.2	4.8	0.0	0	0	0	3.4
90 XB	150	1.2	17.7	11.5	4.8	0.0	0	0	0	3.2
100 XB	170	1.4	17.3	12.5	4.8	0.0	0	0	0	3.0

revisado: 6.2.08

* medido con Uster Tensorapid

** medido con Uster Tester 4

Hermann Bühler AG
Spinnerei
8482 Sennhof (Winterthur)
Schweiz

tel. +41/52/234 04 04
fax +41/52/234 04 94
e-mail: info@buhler yarn.com
internet: www.buhler yarn.com